

# PP複合材料

項目	單位	試驗方法	試驗條件	PP複合材料
		型號		R4340
特性		射出級、尺寸安定性優異、耐衝擊性佳		
		MI(230°C×2.16kg):38		
		Izod(ASTM,1/8"): 9 (23°C)		
		Izod(ASTM,1/8"): 4.5 (-20°C)		
		FM(ASTM):9000		
		TS(ASTM):240		

All tests were run under laboratory conditions, ASTM, ISO testing procedures.  
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649

Address: 11470 台北市內湖區南京東路六段380號A2棟

[www.fcfc-plastics.com](http://www.fcfc-plastics.com)